

Basic Properties of HW Bark

Wood Speciesx	Dry Bark Specific Gravity/Volume	Calorific Value (k cal/kg)
Quaking Aspen	0.73	4685
Black Willow	0.37	3985
Yellow Birch	0.74	5110
Black Willow	0.37	3985
Hackberry	0.65	3970
White Oak	0.68	4035
Red Oak	0.80	4033
White Ash	0.52	4275
Silver Maple	0.67	4645
Yellow-Poplar	0.39	4275
Sweetgum	0.58	4140
Sycamore	0.67	4115