

# Basic Properties of SW Bark

Wood Species	Dry Bark Specific Gravity/Volume	Calorific Value (k cal/kg)
Red Pine	0.32	5039
Loblolly Pine	0.56	5178
Longleaf Pine	0.53	5162
Shortleaf Pine	0.49	5173
Western White Pine	0.62	
Virginia Pine	0.63	
Red Spruce	0.60	
Black Spruce	0.60	4784
Engelmann Spruce	0.68	4644
White Fir	0.62	
Grand Fir	0.61	
Pacific Fir	0.68	
European Larch	0.35	