

BASIC FIBER-SHEET PROPERTIES

Kraft Fiber Resource	Fiber Length/mm	Tear Index*	TEA*	Breaking Length*/km	Zero Span*/km
Northern Bleached SW	2.47	14.1/17.0	10.4/111	1.98/8.10	12.0/15.6
Northern Bleached SW	2.19	15.5/10.3	19.4/126	3.18/9.79	13,4/15.4
Radiata Pine Bleached	2.21	11.3/11.2	9.80/115	1.58/7.58	11.7/15.7
Southern Bleached SW	2.43	12.9/12.1	13.4/110	2.17/7.24	11.4/14.2
Scandinavia Bleached SW	2.20	20.5/12.7	33.6/139	2.64/8.25	12.7/15.7
Southern Bleached HW	0.94	4.53/9.15	4.70/108	1.56/6.58	11.2/13.3
Eucalyptus Bleached	0.76	4.40/10.5	9.28/112	2.16/7.11	13.9/15.6
Acacia Bleached	0.83	2.31/7.54	2.88/87.7	1.35/6.18	11.8/13.4
Aspen Bleached	0.75	3.18/7.82	4.54/88.7	1.64/6.06	11.9/14.6
Birch Bleached	0.91	5.44/7.91	7.27/126	2.12/7.80	12.1/14.8

* Native property and after 4000 PFI refining

ragauskas@hotmail.com