

Kraft Bleached Fiber	Length (mm)	Coarseness (mg/100m)
Western Canadian Northern SW	2.47	20.3
Douglas Fir	2.52	3.19
Eastern Canada Northern SW	2.31	14.3
GA SW	2.44	24.0
Radiate Pine	2.21	22.9
Scandinavia SW	2.20	16.7
Scandinavia Birch	0.91	10.8
Canadian Birch	1.11	12.410.3
Canadian Aspen	0.75	10.3
Georgia HW	0.94	11.9
Eucalyptus Brazilian	0.72	7.45
Acacia	0.66	7.08
Mixed Tropic HW	0.73	6.85
Kenaf	1.04	12.6
Bamboo	1.10	9.31